



## Enkamat<sup>®</sup> 7010W/5/80.30PP

Reinforced grip-layer

### PRODUCT DATA

#### Application

Erosion control

Erosion protection of slopes covered with a geomembrane and steep and/or rocky slopes

#### Product details

Polymer		PA / PP
Color		Black
Mass per unit area	(EN ISO 9864) g/m <sup>2</sup>	510
Thickness	(EN ISO 9863-1) mm	10
Tensile strength (md/cmd) <sup>[1]</sup>	(EN ISO 10319) kN/m	80 / 30
Elongation at break (md/cmd) <sup>[1]</sup>	(EN ISO 10319) %	17.5 / 8.5
Resistance to static puncture	(EN ISO 12236) kN	5
Dynamic perforation (Cone drop)	(EN ISO 13433) mm	8

#### Dimensions

<b>Geocomposite</b>		
Length	m	95
Width	m	4.9
Effective surface	m <sup>2</sup>	465.5
<b>Roll</b>		
Length	m	5.2
Diameter	m	1.15
Gross weight	kg	269

[1] md = machine direction / cmd = cross machine direction.

